

# NITCO

## Tagus Gold (PO)

**Size:** 600 X 600 mm | **Design:** Modern | **Finish:** Glossy Finish in Vitrified SST Body | **Series:** Soluble Salt



Front View



Scale View

### Packaging Details

Size	No. of tiles in box	Coverege Area		Thickness
		sq/mtr	sq/ft	
600 X 600 mm	4.00	1.44	15.50	8.00

### Technical Specification

Sr.No.	Properties	CEN Code	ISO CODE ISO13006:2012E	Requirement for Vitrified Tiles as per Bla Group	NITCO VALUE
1	Deviation in Length %	EN 98	ISO 10545 - 2	±177 0.6 % (Max ±177 2.0 mm)	±177 0.1
2	Deviation in Thickness %	EN 98	ISO 10545 - 2	±77 5.0 % (Max ±177 0.5 mm)	±177 5.0
3	Straightness of Edge %	EN 98	ISO 10545 - 2	±177 0.5 % (Max ±177 1.5 mm)	±177 0.2
4	Diagonal Variation % (Rectangularity)	EN 98	ISO 10545 - 2	±177 0.5 % (Max ±177 2.0 mm)	±177 0.2
5	Surface Flatness %	EN 98	ISO 10545 - 2	±177 0.5 % (Max ±177 2.0 mm)	±177 0.2
6	Surface Quality	EN 98	ISO 10545 - 2	min 95 % free from any Visible Defects	min 95 % free from any Visible Defects
7	Water Absorption % By WT	EN 99	ISO 10545 - 3	< 0.5	< 0.07
8	Modulus of Rupture N/mm <sup>2</sup>	EN 100	ISO 10545 - 4	> 35	> 40
9	Thermal Shock Resistance	EN 104	ISO 10545 - 9	No Visible Defects	Resistant
10	Chemical Resistance (Except HF Acid)	EN 106	ISO 10545 - 13	No Visible Effect	No Visible Effect
11	Resistance To Stain		ISO 10545 - 14	Test Method available	Class 3
12	Deep Abrasion Resistance		ISO 10545 - 6	Max 175 CUBIC MM	Max 175 CUBIC MM
13	Gloss Value			MIN 75 For platinum and > 50 for Diamond	> 80 For platinum and > 55 for Diamond

WANT TO GET IN TOUCH WITH US?

Toll Free: 1800 266 4826 | Email: [marketing@nitco.in](mailto:marketing@nitco.in)